

CLAIMS

1. A modified polyolefin resin produced by subjecting a polyolefin resin (A) to a graft modification by vinyl monomer(s) (B) comprising at least one (meth)acrylate monomer (b) in which
5 an acryloyloxy group or methacryloyloxy group is bonded to a secondary carbon atom or tertiary carbon atom.

2. A modified polyolefin resin composition comprising the modified polyolefin resin defined in claim 1.

10

3. The modified polyolefin resin composition according to claim 2, wherein the vinyl monomer(s) (B) comprises no unsaturated carboxylic acid or its anhydride.

15

4. The polyolefin resin composition according to claim 2, wherein the (meth)acrylate monomer (b) is a compound selected from the group consisting of 4-t-butylcyclohexyl (meth)acrylate, cyclohexyl (meth)acrylate, t-butyl (meth)acrylate, and isobornyl (meth)acrylate.

20

5. The polyolefin resin composition according to claim 2, wherein the vinyl monomer(s) (B) further comprises a monomer having a hydroxyl group in the molecule.

25

6. A resin composition used as a primer for painting and comprising the modified polyolefin resin composition defined

in claim 2.

7. A resin composition used for an adhesive and comprising the modified polyolefin resin composition defined in claim 2.

5

8. A resin composition used for a printing ink and comprising the modified polyolefin resin composition defined in claim 2.